

**Tehničke karakteristike****Korund Braon Al<sub>2</sub>O<sub>3</sub>**

		<b>F12-F30</b>	<b>F36-F80</b>	<b>F90-F180</b>	<b>F220</b>
<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>% min.</b>	<b>94,00</b>	<b>94,50</b>	<b>93,00</b>	<b>93,00</b>
<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>% max.</b>	<b>0,60</b>	<b>0,50</b>	<b>0,70</b>	<b>0,80</b>
<b>TiO<sub>2</sub></b>	<b>% min.</b>	<b>1,80</b>	<b>1,80</b>	<b>1,80</b>	<b>1,80</b>
<b>CaO</b>	<b>% max.</b>	<b>0,80</b>	<b>0,80</b>	<b>0,90</b>	<b>1,10</b>
<b>Količina magnetskih frakcija</b>	<b>% max.</b>	<b>0,20</b>	<b>0,20</b>	<b>0,20</b>	<b>0,20</b>